

**RECEIVED
CENTRAL FAX CENTER****MAR 11 2009**

S/N: 10/550,865

Page 2 of 5

Amendments to the Claims:

This listing of claims will replace all prior versions and listings of claims in the application.

Listing of Claims:

1. (Currently amended) A rubber belt comprising a rubber part and a reinforcing cord embedded in the rubber part, reinforcing cord for rubber reinforcement, comprising wherein the reinforcing cord comprises a carbon fiber strand and a plurality of glass fiber strands arranged around the carbon fiber strand, and
a coating layer containing a rubber is formed on the carbon fiber strand.
2. (Currently amended) The rubber belt reinforcing cord according to claim 1, wherein the total cross section of the carbon fiber strand is in a range of 20% to 80% of the total of the total cross section of the carbon fiber strand and the total cross section of the glass fiber strands.
3. (Currently amended) The rubber belt reinforcing cord according to claim 1, wherein the carbon fiber strand has a twist number of 5.0 times/25 mm or less.
4. (Currently amended) The rubber belt reinforcing cord according to claim 1, wherein surfaces of the glass fiber strands have been treated with a treatment solution containing, as its main components, a rubber latex and a condensate of resorcinol and formalin.
5. (Currently amended) The rubber belt reinforcing cord according to claim 1, wherein the glass fiber strand has been primarily twisted at a twist number in a range of 0.25 to 5.0 times/25 mm.
6. (Currently amended) The rubber belt reinforcing cord according to claim 5, wherein the reinforcing cord has been finally twisted in an opposite direction to a direction in which the glass fiber strand has been primarily twisted.
7. (Currently amended) The rubber belt reinforcing cord according to claim 1, wherein the

S/N: 10/550,865

Page 3 of 5

carbon fiber strand and the glass fiber strand have been primarily twisted in the same direction.

8. (Currently amended) The rubber belt reinforcing cord according to claim 1, wherein a final twist number of the reinforcing cord is in a range of 0.5 to 10 times/25 mm.

9. (Currently amended) The rubber belt reinforcing cord according to claim 1, wherein a surface of the reinforcing cord thereof is covered with rubber.

10-11. Canceled

12. (New) The rubber belt according to claim 1, wherein the coating layer is formed using a treatment solution containing a rubber latex and a mixture of an initial condensate of resorcinol and formalin.